

Multiscale Integrated Numerical Simulation Approach in Štore - Steel Casthouse

*BOŽIDAR ŠARLER, ROBERT VERTNIK, HENRIK GJERKEŠ, AGNIESZKA LORBIECKA,
 **GOJKO MANOJLOVIĆ, JANKO CESAR,
 ***BOJAN MARČIČ, MOJCA SABOLIČ

*Laboratory for Multiphase Processes, University of Nova Gorica, Vipavska 13, SI-5000 Nova Gorica, SLOVENIA

**Technical Development, Štore Steel d.o.o., Železarska cesta 3, SI-3220 Štore, SLOVENIA

***Ates d.o.o., Mroževa ulica 21, SI-2310 Slovenska Bistrica, SLOVENIA

<http://www.p-ng.si>

Abstract: - This paper represents the elements and the use of the simulation system, developed for the Štore-Steel billet caster. The simulation system is used in the context of the state-of-the-art automation and information of the twenty years old three-strand Concast billet continuous caster for dimensions 140, 180, and 220[mm] with the capacity of 150.000[tons/year]. The simulation system is used in the off and in the on-line mode. The off-line mode is used in order to set the proper process parameters and for the redesign of the primary and secondary cooling systems. The numerical solution of the respective models for mass, energy, momentum and species transfer on the macroscopic and on the microscopic scales are based on the recently developed meshless technology. The options of simulation system, which enable the technologist automatic setup of process parameters, are described. The regulation coefficients were calculated based on this simulation system and installed into the casting machine control system. Regulation coefficients are used for compensation of the changes of process parameters that are difficult to control (casting temperature, temperature of cooling water, heat transfer in the mold) with the easily controlled parameters (coolant water flow, casting speed) in such way that the surface temperature and liquid pool depth remain invariant. The computer systems, based on the simulation system and real process parameters data base are described, which help the technologist in estimation of the reasons for possible casting defects and their suppression.

Key-Words: - Continuous casting of steel, simulation system, temperature, velocity, concentration, microstructure, properties, regulation.

1 Introduction

The Štore Steel company is a successor of ironworks which started with the company Berg und Hüttenwerk Štore in the year 1851. State owned Jeklo Štore has been sold to Inexa from Sweden and Unior from Slovenia in 1999 and renamed to Inexa Štore. Unior bought shares from Inexa and sold its previous shares to Slovene partner companies Kovintrade and Dinos Celje in year 2003. The company afterwards received his present name Štore - Steel. It has around 490 employees and is ranking on the place fifty among Slovenian companies regarding the quantity of export towards developed markets. The production focus is on rounds and flats of small and medium size. Plant capacities enable a long - term production of 120.000 to 140.000 tons per year. Such quantities are not sufficient to achieve cost efficiency on the basis of economies of the scale but are ideal for covering of market niches where special needs exist. The company is respectively producing a huge spectrum of different

high quality steels in relatively small amounts. The company has a long tradition in delivering top quality steels to the major European spring and automotive producers. Every third truck, produced in Europe, is respectively driving on the springs, produced from the Štore - Steel semi-products. The Company is an ISO-9001 certified mini-mill using steel scrap as the main resource for steel production. The steel plant consists of EAF furnace, ladle furnace VOD-VD, and three-strand bow type CC machine. The business strategy of the company has the following basic goals: (I) to increase selling of company products and services, based on higher quality and productivity, (II) permanent restructuring and modernisation of the company, (III) just in time strategy, (IV) optimisation of the efficiency and effectiveness of the human resources, (V) minimisation of the environmental impact, (VI) stimulation of the in - factory and global technological development through major expansion of research and development on local and European

level. In year 1999 the company started a major CC billet caster modernisation programme. The final goal of the programme which has been completed within the EU project COST-526: Automatic Process Optimisation in Materials Technology (APOMAT) in 2005 is the state-of-the-art information [1] of the caster. The following four general strategies have been chosen in order to improve the quality of the product and the safety and the economy of the continuous casting process at Štore - Steel: (I) better understanding of the process, (II) better insight into the process, (III) better influence on the process, (IV) better organization of the work around the process.

2 New Control System

The control system of the Štore - Steel caster has been designed in order to address the second and the third principal tasks. The system consists of four elements: (I) operator control console with man - machine interface (MMI), (II) programmable logic controller (PLC), (III) associated custom software, and (IV) field devices (sensors, actuators). The benefits of the installed control system include: (I) increased productivity through controlled, repeatable cast starts and stops and ability to develop and optimise casting practices, (II) increased recovery through reduced operator error, (III) improved safety due to the controlled cast starts, stops and emergency procedures, (IV) increased consistency of metal properties from cast to cast, (V) most importantly, the casting control system is based on intimate knowledge and a thorough understanding of the CC machine, gained in the last twenty years of operation. The details of the system are given in [2]. All sensors of the CC machine have been renewed, replaced or upgraded. Additional sensors have been installed in order to achieve a detailed insight into casting temperature, velocity, mould oscillation, mould level, primary and secondary coolant system flows, pressures, and temperatures. On-line pyrometers have been installed before unbending region and several more are planned in upwards direction. All the cooling system flows have been made controllable from the man-machine interface and no manual valve operations are needed any more. Because the system has been developed in collaboration with the plant process engineers and a domestic automation company, several modifications of the system already took place and additional might be planned in a most straightforward and easy manner.

3 Process Modelling

Mathematical process models can be applied in several different ways to serve industry by inducing beneficial changes to process operation. CC process modelling [3,4] has been introduced at Štore STEEL in order to improve quality, reduce production cost, and improve safety. Like most commercial material processes, the continuous casting involves many interacting phenomena of great complexity. Because of this complexity, no model can include all of the involved phenomena at once. Two following two types of models are continuously under development: off-line and on-line CC model.

3.1 The off-Line CC Model

3.1.1 Temperatures

The off-line CC model calculates the steady temperature distribution in the strand as a function of the following process parameters: billet dimension, steel grade, casting temperature, casting velocity, primary, and two secondary cooling systems flows, pressures, temperatures, type and quantity of the casting powder, and the (non)application of the radiation shield and electromagnetic stirring. The Bennon-Incropera mixture continuum formulation is used for the physical model, solved by the Voller-Swaminathan iterative scheme. The recently developed meshless Local Radial Basis Function Collocation Method (LRBFCM) [5,6,7,8] is used for the solution of thermal and stress-strain fields with non-uniform mesh discretization in all three dimensions. In this novel numerical method, the domain and boundary of interest are divided into overlapping influence areas. On each of them, the fields are represented by the multiquadrics radial basis function collocation on a related sub-set of nodes. Time-stepping is performed in an explicit way. The governing equations are solved in its strong form, i.e. no integrations are performed. The polygonisation is not present and the method is practically independent on the problem dimension. Scheme of the simulation system is depicted in Figure 1. Different steel material properties generation packages [9,10] might be directly attached to the temperature and stress field solver. The thermal conductivity of the liquid phase is artificially enhanced to account for the forced and natural convection effects in the melt. The simulation output is represented in graphical (around 50 pictures) and

alphanumeric form. The results include plots of the used steel grade enthalpy, specific heat, thermal conductivity, density, thermal contraction, differential thermal contraction, dynamic liquid viscosity, liquid phase fraction, a log file of all generated material properties, and a schematic caster geometry plot. The temperature and phase field graphics include corner, centreline, and average temperatures of the four billet surfaces, longitudinal and transversal temperatures and phase fractions of the billet and an overview of all other typical technological strand data in alphanumeric form. The alphanumeric output includes maximum, average and minimum temperatures of billet surfaces and edges at different longitudinal caster segments. The heat transport mechanisms in the mould take into account the heat transport mechanisms through the casting powder, across the air-gap (if it exists), to the mould surface, in the mould, and from the mould inner surface to the mould cooling water. The heat transport mechanisms in the secondary cooling zone take into account the effects of the casting velocity, strand surface temperature, spray nozzle type, spray water flow, temperature and pressure, radiation and cooling through the rolls contact. Different types of the rolls are considered (driving, passive, centrally cooled, externally cooled, etc.). The mentioned basic heat transfer mechanisms are modified with regard to running water and rolls stagnant water at relevant positions. All involved heat transport mechanisms have been implemented as generic at the first stage of the simulator development. They have been systematically replaced by the plant specific ones through data from the plant measurements and laboratory measurements [11].

3.1.2 Temperatures and velocities

The velocity model has been recently added to the temperature model by incorporating the solution of the coupled heat, mass and momentum transport. The governing equations are based on the mixture continuum formulation of the solid and the liquid phase. The model takes into account the pure liquid, nucleation and movement of the globulitic solid phase, formation of the rigid porous solid matrix, and complete solid. The most simple zero-equation Prandtl mixing-length theory turbulence model is incorporated into the momentum equation [12]. This models allows for more precise simulation of the heat transfer in the mould as a function of the submerged entry nozzle position.

3.1.3 Temperatures, velocities and concentration

The inner structure of the continuously cast billets has a great importance from the point of view of

further processing and application. The main reason for this is the very direct effect of the inner structure's features (ie. porosity, macrosegregations, geometry of primary dendrites) on the technological characteristics of further processing (ie. crack sensitivity, formability, etc.). The columnar to equiaxed transition position and the extent of macrosegregation are being included in the form of semi-empirical correlations, developed in [13].

3.1.4 Microstructure

A physically and mathematically more sound approach is being recently adopted through the coupling of the macroscopic temperature and velocity fields with the cellular automaton approach to incorporate the phase transformation kinetics effects and thus predict the size and orientation of the grains [14].

3.1.5 Thermomechanics

One of the major problems encountered in continuous casting process is the formation of surface and internal cracks and the shape deformation [15]. These cracks are results of thermo-mechanically induced strains and stresses due to high temperature gradients and density changes, effects of ferrostatic pressure, gravitational self-loading of the billet and other mechanically (straightening machine) induced loads. In 2004 a programme of complementing the thermal calculations with the mechanical ones started. Thermo-mechanically induced strains can be calculated as a sum of the strains induced by temperature and phase changes, the ferrostatic pressure and the mechanical loadings (gravitational, etc), respectively. In the same manner, the calculations can be divided in the three main entities: calculation of the thermal and phase-change induced strains, calculation of the strains induced by the ferrostatic pressure and the calculations of the strains induced by the gravitational and other mechanical loadings. The ferrostatic pressure, which depends of the "height" of the liquid metall is also a mechanical load, but its calculation is separated for better understanding of particular effects. On the other hand, at high temperatures, the material behaviour is highly nonlinear, so the nonlinear elastic - viscoplastic temperature dependent material model has to be used. As the thermal and mechanical problems are strongly coupled, their calculation could not be separated in a general case. For example, the mechanical state variables depend on the temperature field and heat transfer coefficients in the mould depend on the air gap, which makes temperature field strongly dependent

on displacement. Thus, the calculation of the distribution of temperature, strains and stresses have to be calculated in a time-dependent iterative manner in the future [16]. All the details mentioned above enlarge complexity of the model and computational costs. At this stage, only the steady-state elastic calculations were made. The deformation model of the billet in the mould, which is currently the sole simulation system integrated mechanical module, is used as a help for technologists in order to decide about the appropriate mould taper. The simulation system has a user-friendly self-explanatory Windows application for generation of the simulation and plot input data as well a self-explanatory plot results browser. A dynamic model of the strand with the dynamic plot browser is available as well.

3.2 The on-line CC model

3.2.1 Automation

The on-line CC model is used exclusively in automation of the CC machine. It controls the mould oscillation, electromagnetic stirring, casting speed, and spray flows as a function of format, steel grade, casting temperature, start and stop of the cast. The regulation algorithm is based on the sensitivity coefficients derived from the off-line CC model. The principal control strategy is based on compensation of the process parameters that are difficult to control (casting temperature, cooling water temperature, mould heat extraction) with the casting parameters that are more easy to control (casting speed, spray water flow) in order to preserve the reasonable similar surface temperature and metallurgical length. The regulation coefficients of the on-line CC model are calculated from the off-line CC model of the temperature field.

3.2.2 Monitoring of process parameters

The on-line "caster status model" was developed and implemented on the plant that shows the current status of the casting machine, particularly the temperature at the unbending point, metallurgical length and the thickness of the solid shell at the outlet of the mould. This graphical presentation is entirely based on the regulation coefficients.

3.3 Post - processing

The post-processing of the stored caster process parameters data is made in two different ways. In the first way, the "caster status model" is run after

the casting with the realistic casting data and the technological parameters are graphically represented as a function of time or casted length. In the second approach, the full transient temperature model in realistic geometry is run with realistic casting data and a full transient presentation of the casting temperature field is made.

4 Process Optimisation

Continuously cast billets are subject to several different types of quality problems. Their quality is determined by the desired composition and cleanliness of the melt, by the expected shape and surface smoothness of the final product, and by as low as possible cracking, macro- and micro-segregation. The experience gained during continuous casting of steel evolved in empirical metallurgical cooling criteria for the process [17]. Present authors have further developed this criteria for several years from the basic set [18] and what follows represents their fourth improved and enhanced generation. They are listed in quality, safety, economy, ecology and maintenance categories: Quality: (I) maximum depth of the liquid pool, (II) maximum billet surface cooling rate in the spray cooling zone, (III) maximum billet surface reheating rate in the spray cooling zone, (IV) maximum billet surface temperature in the unbending region, (V) maximum negative billet surface deviation at given axial position, (VI) maximum positive billet surface deviation at a given axial position; Safety: (VII) minimum safety thickness of the steel crust at the mould outlet, maximum safety depth of the liquid pool; Economy: (VIII) maximum casting speed, (IX) minimum superheat; Ecology: (X) minimum consumption of spray water; Maintenance: (XI) minimum forces on the rolls and unbending machine. It is believed that the consideration of the listed criteria leads to the best product quality, best caster safety, best caster economy, best caster ecology, and longest caster maintenance intervals. Based on the calculation of the temperature distribution in the billet, the metallurgical cooling criteria can be explicitly evaluated. The technologist has an opportunity to search for the weak points of the process parameter setting. Using the simulator, he is able to properly tailor all process parameters. This is much easier, safer and cost-effective than real-word experimentation. Such simulation is of pronounced importance when designing the process parameter settings for the continuous casting of new materials. With the heat transfer model, the design changes on

the plant such as change of the rolls, spray nozzle type, etc., can be easily tested. The heat transfer model can straightforwardly answer to some of the important safety questions. For example, can a pressure drop in one of the cooling systems cause a breakout, etc. In addition, it is extremely useful for training of the caster operators. The simulation system has been already successfully employed for casting practice design and for the design modifications of the secondary cooling system. These modifications include installation of additional spray nozzles which suppressed the corner cracking in some of the steel grades and dimensions. As the number of possible process parameters is high and the criteria are highly conflicting, determining appropriate values is not trivial. A novel approach [18] to process parameter optimisation is in the implementation in the presented simulation system. The approach relies on the heat transfer model, metallurgical cooling criteria and a genetic algorithm, which is a stochastic optimisation method from the field of evolutionary computation. The system iteratively and automatically improves the parameter settings: the genetic algorithm guides the search through the parameter space and activates the heat transfer model to evaluate the candidate parameter settings. The continuous casting process has a substantial optimisation potential because the process involves many input parameters which are almost impossible to set optimally through experimentation only. Despite the developed very sophisticated and comprehensive automatic process optimisation framework, only two automatic process model options are currently implemented in practice: automatic set-up of process parameters that yields predetermined metallurgical length or surface temperature.

5 Further Process Automation

The primary task of further plant automation represents development and calibration of the simulator (experimental programme) and proper, steel specific definition of optimisation criteria as well as proper definition of optimisation problem as a whole (interaction of different optimisation categories in order to achieve optimum yield). The optimiser, based on the hybrid evolutionary computation approach, developed in [19] will be used. The dynamic process parameters setting in continuous casting is a task first achieved almost 20 years ago [17], however, the dynamic optimum control of the process parameters setting is a task yet

to be achieved. For this purpose new, very fast simulation and optimisation algorithms have to be developed in order to achieve the computing times of one to five seconds per optimisation/regulation step. The development of such algorithms in realistic geometry is representing one of the principal ongoing research tasks.

6 Conclusions

The described information of the Štore – Steel billet caster substantially improved the process performance [20]. Successful model implementation requires skills in at least two different fields: practical understanding of the industrial process and computer modelling. In the present case the developments represent results of six research teams: the first is specialised in numerical modelling and computer graphics connected to the casting processes, the second in plant specific technology and expert knowledge, the third in industrial automation, the fourth in optimisation procedures, the fifth in plant and laboratory measurements, and the sixth in the development of optimisation criteria. The described elements of the upgrades, particularly full off- and on-line automatic optimisation, will be stepwise implemented in the near future. The described elements of the caster information will be demonstrated in detail at the conference.

7 Acknowledgement

The described work has been done in the framework of a number of interconnected projects in years 2000 - 2006, sponsored by the Štore - Steel company, Slovenian Ministry for High Education, Science and Technology, bilateral Slovene - Czech project: Modelling and Simulation for Competitive Continuous Casting, bilateral Slovene – Hungarian Project Macrosegregation in Continuous Casting of Steel, EU sponsored projects COST-526: Automatic Process Optimisation in Materials Technology and INSPIRE.

References:

- [1] B.G. Thomas, Comments on the industrial application of process models, In: V.R.Voller, S.P.Marash, N.El-Kaddah (Eds.), *Materials Processing in the Computer Age II*, TMS, Warrendale, 1994, pp.3-20.
- [2] B. Šarler, R. Vertnik, G. Manojlović, J. Cesar, M. Sabolič, I. Justinek, B. Marčič, B. Filipič, M. Raudensky, J. Horsky, E. Laitinen,

- Informatisation upgrades of the INEXA-ŠTÖRE billet caster, In: *4th International Metallurgical Conference on Continuous Casting of Billets*, 30th, 31st October and 1st November 2001, Trinec Czech Republic, Česká Hutnická Společnost, 2001, pp.17-26.
- [3] B. Šarler, B. Filipič, M. Raudensky, J. Horsky, An interdisciplinary approach towards optimum continuous casting of steel, In: V.R.Voller, H. Henein (Eds.), *Materials Processing in the Computer Age III*, TMS, Warrendale, 2000, pp.27-36.
- [4] M. Rappaz, M. Kedro (Eds.), Modelling in Materials Science and Processing, *Proceedings of the general COST-512 workshop*, European Commission, Brussels, 1996.
- [5] B. Šarler, R. Vertnik, J. Perko, Application of diffuse approximate method in convective-diffusive solidification problems, *Computers, Materials, Continua*, Vol.2, 2005, pp.77-83.
- [6] B. Šarler, R.Vertnik, Meshfree local radial basis function collocation method for diffusion problems. *Computers and Mathematics with Application*, Vol. 51, 2006, pp. 1269-1282
- [7] R. Vertnik, B. Šarler, Meshless local radial basis function collocation method for convective-diffusive solid-liquid phase change problems. *International Journal of Numerical Methods for Heat & Fluid Flow*, 2006, vol.16, no. 5, str. 617-640.
- [8] R. Vertnik, M. Založnik, B. Šarler, Solution of transient direct-chill aluminium billet casting problem with simultaneous material and interphase moving boundaries by a meshless method. *Engineering Analysis with Boundary Elements*, Vol. 30, 2006, pp. 847-855.
- [9] J. Miettinen, Calculation of solidification-related thermophysical properties for liquid steels, *Metall. Mater.Trans.*, Vol.28B, 1991, pp.175-189.
- [10] N. Saunders, X. Li, P. Miodownik, J.Ph. Schille, Using JmatPro to model materials properties and behavior, *Journal of Metals*, Vol.55, 2003, pp.60-65.
- [11] J. Horský, M. Raudenský, Experimental study of nozzle cooling in continuous casting, In: *2nd International Conference Continuous Casting of Billets*, Trinec, 1997, pp.99-106.
- [12] B. Šarler, R.Vertnik, G.Manojlović,, A meshless solution procedure for coupled turbulent flow and solidification in steel billet casting. In: C.A. Brebbia, J.T. Katsikadelis (Eds.). *Boundary Elements and Other Mesh Reduction Methods XXVIII*, WIT Press, 2006, pp. 131-142.
- [13] M.Reger, B.Vero, H.Kytonen, S.Louhenkilpi, A.Szelig, Macrostructure prediction of CC slabs, *Materials Science Forum*, Vol.473, 2005, pp.375-380.
- [14] S.Kundu, M.Dutta, S.Ganguly, S. Chandra, Prediction of phase transformation and microstructure in steel using cellular automaton technique, *Scripta Materialia*, Vol.50, 2004, pp.891-895.
- [15] A.H. Huespe, A. Cardone, V. Fachinotti, Thermomechanical model of a continuous casting process, *Computer Methods in Applied Mechanics and Engineering*, Vol.182, 2000, pp.439-455.
- [16] J. R. Boehmer, F. N. Fett, G. Funk, Analysis of high temperature behavior of solidified material within a continuous casting machine, *Computers and Structures*, Vol.47, 1993, pp.683-698.
- [17] E. Laitinen, On the simulation and control of the continuous casting process, Ph.D. Thesis, University of Jyvaskila, Finland, 1989.
- [18] B. Filipič, B. Šarler, E. Šubelj, Evolutionary optimisation of continuous casting at the ACRONI (Slovenia) steelworks, *EvoNews*, Vol.2, 1996, pp.16-18.
- [19] B. Filipič, T. Robič, A comparative study of coolant flow optimization on a steel casting machine. *Proceedings of the 2004 Congress on Evolutionary Computation CEC 2004*, Portland, OR, USA. IEEE, Piscataway, Vol.1, pp. 569-573.
- [20] B. Šarler, R, Vertnik, S. Šaletić, G. Manojlović, CESAR, J. Cesar, Application of continuous casting simulation at Štore Steel. *Berg-Huettenmaennische Monatshefte*, Vol. 150, 2005, pp. 300-306.